



IEC 60227-5

Edition 4.0 2024-02
REDLINE VERSION

INTERNATIONAL STANDARD



**Polyvinyl chloride insulated cables of rated voltages up to and including
450/750 V –
Part 5: Flexible cables (cords)**

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

ICS 29.060.20

ISBN 978-2-8322-8370-7

Warning! Make sure that you obtained this publication from an authorized distributor.

CONTENTS

FOREWORD.....	5
INTRODUCTION.....	2
1 General.....	8
1 Scope.....	8
2 Normative references	8
3 Terms and definitions	10
4 Flat tinsel cord.....	10
4.1 Code designation.....	10
4.2 Rated voltage	10
4.3 Construction	10
4.3.1 Conductors.....	10
4.3.2 Insulation.....	10
4.3.3 Assembly of cores	11
4.3.4 Overall dimensions	11
4.4 Tests	11
4.4.1 General	11
4.4.2 Bending test	11
4.4.3 Drop test	11
4.5 Guidance on use.....	11
5 (Vacant)	12
6 Cord for indoor decorative lighting chains.....	12
6.1 Code designation.....	12
6.2 Rated voltage	12
6.3 Construction	12
6.3.1 Conductors.....	12
6.3.2 Insulation.....	13
6.3.3 Cord identification.....	13
6.3.4 Overall diameter	13
6.4 Tests	13
6.4.1 General	13
4.4.2 Long term resistance of insulation to d.c.....	13
6.4.2 (Vacant)	13
6.5 Guidance on use.....	14
7 Light polyvinyl chloride sheathed cord	15
7.1 Code designation.....	15
7.2 Rated voltage	15
7.3 Construction	15
7.3.1 Conductors.....	15
7.3.2 Insulation.....	16
7.3.3 Assembly of cores	16
7.3.4 Sheath.....	16
7.3.5 Overall dimensions	16
7.4 Tests	16
7.4.1 General	16
7.4.2 Flexing test.....	16
7.5 Guidance on use.....	16

8	Ordinary polyvinyl chloride sheathed cord	18
8.1	Code designation	18
8.2	Rated voltage	19
8.3	Construction	19
8.3.1	Conductors	19
8.3.2	Insulation.....	19
8.3.3	Assembly of cores and fillers, if any.....	19
8.3.4	Sheath.....	19
8.3.5	Overall dimensions	19
8.4	Tests	20
8.4.1	General	20
8.4.2	Flexing test.....	20
8.5	Guidance on use.....	20
9	Heat-resistant light PVC-sheathed cord for a maximum conductor temperature of 90 °C.....	23
9.1	Code designation	23
9.2	Rated voltage	23
9.3	Construction	23
9.3.1	Conductors	23
9.3.2	Insulation.....	23
9.3.3	Assembly of cores	23
9.3.4	Sheath.....	23
9.3.5	Overall dimensions	23
9.4	Tests	24
9.4.1	General	24
9.4.2	Flexing test.....	24
9.5	Guidance on use.....	24
10	Heat-resistant ordinary PVC-sheathed cord for a maximum conductor temperature of 90 °C.....	26
10.1	Code designation	26
10.2	Rated voltage	26
10.3	Construction	26
10.3.1	Conductors	26
10.3.2	Insulation.....	26
10.3.3	Assembly of cores and fillers, if any.....	26
10.3.4	Sheath.....	27
10.3.5	Overall dimensions	27
10.4	Tests	28
10.4.1	General	28
10.4.2	Flexing test.....	28
10.5	Guidance on use.....	28
	Bibliography.....	28
	Table 1 – General data for type 60227 IEC 41	11
	Table 2 – Tests for type 60227 IEC 41	12
	Table 3 – General data for type 60227 IEC 43	14
	Table 4 – Tests for type 60227 IEC 43.....	15

Table 5 – Mass of weight and diameter of pulleys	17
Table 6 – General data for type 60227 IEC 52	17
Table 7 – Tests for type 60227 IEC 52	18
Table 8 – General data for type 60227 IEC 53	20
Table 9 – Mass of weight and diameter of pulleys	21
Table 10 – Tests for type 60227 IEC 53	22
Table 11 – Mass of weight and diameter of pulleys	24
Table 12 – General data for type 60227 IEC 56	25
Table 13 – Tests for type 60227 IEC 56	25
Table 14 – General data for type 60227 IEC 57	27
Table 15 – Mass of weight and diameter of pulleys	28
Table 16 – Tests for type 60227 IEC 57	30

INTERNATIONAL ELECTROTECHNICAL COMMISSION

**POLYVINYL CHLORIDE INSULATED CABLES
OF RATED VOLTAGES UP TO AND INCLUDING 450/750 V –****Part 5: Flexible cables (cords)**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as “IEC Publication(s)”). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) IEC draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). IEC takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, IEC had not received notice of (a) patent(s), which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at <https://patents.iec.ch>. IEC shall not be held responsible for identifying any or all such patent rights.

This redline version of the official IEC Standard allows the user to identify the changes made to the previous edition IEC 60227-5:2011. A vertical bar appears in the margin wherever a change has been made. Additions are in green text, deletions are in strikethrough red text.

IEC 60227-5 has been prepared by IEC technical committee 20: Electric cables. It is an International Standard.

This fourth edition cancels and replaces the third edition published in 2011. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- a) the reference to tests according to IEC 60227-2 has been withdrawn and replaced with a reference to IEC 63294;
- b) normative references have been updated.

The text of this International Standard is based on the following documents:

Draft	Report on voting
20/2143/FDIS	20/2156/RVD

Full information on the voting for its approval can be found in the report on voting indicated in the above table.

The language used for the development of this International Standard is English.

This document was drafted in accordance with ISO/IEC Directives, Part 2, and developed in accordance with ISO/IEC Directives, Part 1 and ISO/IEC Directives, IEC Supplement, available at www.iec.ch/members_experts/refdocs. The main document types developed by IEC are described in greater detail at www.iec.ch/publications.

A list of all parts in the IEC 60227 series, published under the general title *Polyvinyl chloride insulated cables of rated voltages up to and including 450/750 V*, can be found on the IEC website.

This document is to be used in conjunction with IEC 60227-1:—¹.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under webstore.iec.ch in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn, or
- revised.

IMPORTANT – The "colour inside" logo on the cover page of this document indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.

¹ Fourth edition under preparation. Stage at the time of publication IEC FDIS 60227-1:2023.

INTRODUCTION

The IEC 60227 series, published under the general title *Polyvinyl chloride insulated cables of rated voltages up to and including 450/750 V*, consists of the following parts:

IEC 60227-1, General requirements;

IEC 60227-2, Test methods (withdrawn and replaced by IEC 63294);

IEC 60227-3, Non-sheathed cables for fixed wiring;

IEC 60227-4, Sheathed cables for fixed wiring;

IEC 60227-5, Flexible cables (cords);

IEC 60227-6, Lift cables and cables for flexible connections;

IEC 60227-7, Flexible cables screened and unscreened with two or more conductors and of rated voltages up to and including 300/500 V.

This part of IEC 60227, when used in conjunction with IEC 60227-1, forms the complete standard for flexible cables (cords).

POLYVINYL CHLORIDE INSULATED CABLES OF RATED VOLTAGES UP TO AND INCLUDING 450/750 V –

Part 5: Flexible cables (cords)

~~1 General~~

1 Scope

This part of IEC 60227 details the particular specifications for polyvinyl chloride insulated flexible cables (cords), of rated voltages up to and including 300/500 V.

~~All cables comply with the appropriate requirements given in IEC 60227-1 and each individual type of cable complies with the particular requirements of this part.~~

This document provides the particular requirements for flexible cables (cords) which apply in addition to the appropriate requirements specified in IEC 60227-1, which apply to all cables.

The tests for cables specified in the IEC 60227 series are described in IEC 63294.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

~~NOTE—The IEC 60811 series is currently undergoing a revision, which will lead to a restructuring of its parts. A description of this, as well as a cross-reference table between the current and planned parts will be given in IEC 60811-100.~~

IEC 60227-1:2007², *Polyvinyl chloride insulated cables of rated voltages up to and including 450/750 V – Part 1: General requirements*

~~IEC 60227-2:1997, *Polyvinyl chloride insulated cables of rated voltages up to and including 450/750 V – Part 2: Test methods*
Amendment 1 (2003)~~

IEC 60228, *Conductors of insulated cables*

IEC 60332-1-2, *Tests on electric and optical fibre cables under fire conditions – Part 1-2: Test for vertical flame propagation for a single insulated wire or cable – Procedure for 1 kW pre-mixed flame*

~~IEC 60811-1-1:1993, *Common test methods for insulating and sheathing materials of electric cables – Part 1: Methods for general application – Section 1: Measurement of thickness and overall dimensions – Tests for determining the mechanical properties*
Amendment 1 (2001)~~

² Fourth edition under preparation. Stage at the time of publication IEC FDIS 60227-1:2023.

~~IEC 60811-1-2:1985, Common test methods for insulating and sheathing materials of electric cables – Part 1: Methods for general application – Section Two: Thermal ageing methods
Amendment 1 (1989)
Amendment 2 (2000)~~

~~IEC 60811-1-4:1985, Common test methods for insulating and sheathing materials of electric cables – Part 1: Methods for general application – Section Four: Tests at low temperature
Amendment 1 (1993)
Amendment 2 (2001)~~

~~IEC 60811-3-1:1985, Common test methods for insulating and sheathing materials of electric cables – Part 3: Methods specific to PVC compounds – Section One: Pressure test at high temperature – Tests for resistance to cracking
Amendment 1 (1994)
Amendment 2 (2001)~~

~~IEC 60811-3-2:1985, Common test methods for insulating and sheathing materials of electric cables – Part 3: Methods specific to PVC compounds – Section Two: Loss of mass test – Thermal stability test
Amendment 1 (1993)
Amendment 2 (2003)~~

IEC 60811-401, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 401: Miscellaneous tests – Thermal ageing methods – Ageing in an air oven*

IEC 60811-405, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 405: Miscellaneous tests – Thermal stability test for PVC insulations and PVC sheaths*

IEC 60811-409, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 409: Miscellaneous tests – Loss of mass test for thermoplastic insulations and sheaths*

IEC 60811-501, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 501: Mechanical tests – Tests for determining the mechanical properties of insulating and sheathing compounds*

IEC 60811-504, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 504: Mechanical tests – Bending tests at low temperature for insulation and sheaths*

IEC 60811-505, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 505: Mechanical tests – Elongation at low temperature for insulations and sheaths*

IEC 60811-506, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 506: Mechanical tests – Impact test at low temperature for insulations and sheaths*

IEC 60811-508, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 508: Mechanical tests – Pressure test at high temperature for insulation and sheaths*

IEC 60811-509, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 509: Mechanical tests – Test for resistance of insulations and sheaths to cracking (heat shock test)*

IEC 62440, *Electric cables with a rated voltage not exceeding 450/750 V – Guide to use*

IEC 63294:2021, *Test methods for electric cables with rated voltages up to and including 450/750 V.*

INTERNATIONAL STANDARD

**Polyvinyl chloride insulated cables of rated voltages up to and including
450/750 V –
Part 5: Flexible cables (cords)**



CONTENTS

FOREWORD.....	5
INTRODUCTION.....	7
1 Scope.....	8
2 Normative references	8
3 Terms and definitions	9
4 Flat tinsel cord.....	9
4.1 Code designation.....	9
4.2 Rated voltage	9
4.3 Construction	10
4.3.1 Conductors.....	10
4.3.2 Insulation.....	10
4.3.3 Assembly of cores	10
4.3.4 Overall dimensions	10
4.4 Tests	10
4.4.1 General	10
4.4.2 Bending test	10
4.4.3 Drop test	10
4.5 Guidance on use.....	10
5 (Vacant)	11
6 Cord for indoor decorative lighting chains.....	11
6.1 Code designation.....	11
6.2 Rated voltage	12
6.3 Construction	12
6.3.1 Conductors.....	12
6.3.2 Insulation.....	12
6.3.3 Cord identification.....	12
6.3.4 Overall diameter	12
6.4 Tests	12
6.4.1 General	12
6.4.2 (Vacant)	12
6.5 Guidance on use.....	12
7 Light polyvinyl chloride sheathed cord	14
7.1 Code designation.....	14
7.2 Rated voltage	14
7.3 Construction	14
7.3.1 Conductors.....	14
7.3.2 Insulation.....	14
7.3.3 Assembly of cores	14
7.3.4 Sheath.....	14
7.3.5 Overall dimensions	14
7.4 Tests	14
7.4.1 General	14
7.4.2 Flexing test.....	15
7.5 Guidance on use.....	15
8 Ordinary polyvinyl chloride sheathed cord	16
8.1 Code designation.....	16

8.2	Rated voltage	17
8.3	Construction	17
8.3.1	Conductors	17
8.3.2	Insulation.....	17
8.3.3	Assembly of cores and fillers, if any	17
8.3.4	Sheath.....	17
8.3.5	Overall dimensions	17
8.4	Tests	18
8.4.1	General	18
8.4.2	Flexing test.....	18
8.5	Guidance on use.....	19
9	Heat-resistant light PVC-sheathed cord for a maximum conductor temperature of 90 °C.....	20
9.1	Code designation.....	20
9.2	Rated voltage	20
9.3	Construction	20
9.3.1	Conductors	20
9.3.2	Insulation.....	21
9.3.3	Assembly of cores	21
9.3.4	Sheath.....	21
9.3.5	Overall dimensions	21
9.4	Tests	21
9.4.1	General	21
9.4.2	Flexing test.....	21
9.5	Guidance on use.....	22
10	Heat-resistant ordinary PVC-sheathed cord for a maximum conductor temperature of 90 °C.....	24
10.1	Code designation.....	24
10.2	Rated voltage	24
10.3	Construction	24
10.3.1	Conductors	24
10.3.2	Insulation.....	24
10.3.3	Assembly of cores and fillers, if any	24
10.3.4	Sheath.....	24
10.3.5	Overall dimensions	24
10.4	Tests	25
10.4.1	General	25
10.4.2	Flexing test.....	25
10.5	Guidance on use.....	26
	Bibliography.....	28
	Table 1 – General data for type 60227 IEC 41	11
	Table 2 – Tests for type 60227 IEC 41	11
	Table 3 – General data for type 60227 IEC 43	13
	Table 4 – Tests for type 60227 IEC 43.....	13
	Table 5 – Mass of weight and diameter of pulleys	15
	Table 6 – General data for type 60227 IEC 52	15

Table 7 – Tests for type 60227 IEC 52.....	16
Table 8 – General data for type 60227 IEC 53	18
Table 9 – Mass of weight and diameter of pulleys	19
Table 10 – Tests for type 60227 IEC 53	19
Table 11 – Mass of weight and diameter of pulleys	22
Table 12 – General data for type 60227 IEC 56	22
Table 13 – Tests for type 60227 IEC 56	23
Table 14 – General data for type 60227 IEC 57	25
Table 15 – Mass of weight and diameter of pulleys	26
Table 16 – Tests for type 60227 IEC 57	26

INTERNATIONAL ELECTROTECHNICAL COMMISSION

**POLYVINYL CHLORIDE INSULATED CABLES
OF RATED VOLTAGES UP TO AND INCLUDING 450/750 V –****Part 5: Flexible cables (cords)**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as “IEC Publication(s)”). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) IEC draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). IEC takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, IEC had not received notice of (a) patent(s), which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at <https://patents.iec.ch>. IEC shall not be held responsible for identifying any or all such patent rights.

IEC 60227-5 has been prepared by IEC technical committee 20: Electric cables. It is an International Standard.

This fourth edition cancels and replaces the third edition published in 2011. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- a) the reference to tests according to IEC 60227-2 has been withdrawn and replaced with a reference to IEC 63294;
- b) normative references have been updated.

The text of this International Standard is based on the following documents:

Draft	Report on voting
20/2143/FDIS	20/2156/RVD

Full information on the voting for its approval can be found in the report on voting indicated in the above table.

The language used for the development of this International Standard is English.

This document was drafted in accordance with ISO/IEC Directives, Part 2, and developed in accordance with ISO/IEC Directives, Part 1 and ISO/IEC Directives, IEC Supplement, available at www.iec.ch/members_experts/refdocs. The main document types developed by IEC are described in greater detail at www.iec.ch/publications.

A list of all parts in the IEC 60227 series, published under the general title *Polyvinyl chloride insulated cables of rated voltages up to and including 450/750 V*, can be found on the IEC website.

This document is to be used in conjunction with IEC 60227-1:—¹.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under webstore.iec.ch in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn, or
- revised.

¹ Fourth edition under preparation. Stage at the time of publication IEC FDIS 60227-1:2023.

INTRODUCTION

The IEC 60227 series, published under the general title *Polyvinyl chloride insulated cables of rated voltages up to and including 450/750 V*, consists of the following parts:

IEC 60227-1, General requirements;

IEC 60227-2, Test methods (withdrawn and replaced by IEC 63294);

IEC 60227-3, Non-sheathed cables for fixed wiring;

IEC 60227-4, Sheathed cables for fixed wiring;

IEC 60227-5, Flexible cables (cords);

IEC 60227-6, Lift cables and cables for flexible connections;

IEC 60227-7, Flexible cables screened and unscreened with two or more conductors and of rated voltages up to and including 300/500 V.

This part of IEC 60227, when used in conjunction with IEC 60227-1, forms the complete standard for flexible cables (cords).

POLYVINYL CHLORIDE INSULATED CABLES OF RATED VOLTAGES UP TO AND INCLUDING 450/750 V –

Part 5: Flexible cables (cords)

1 Scope

This part of IEC 60227 details the particular specifications of polyvinyl chloride insulated flexible cables (cords), of rated voltages up to and including 300/500 V.

This document provides the particular requirements for flexible cables (cords) which apply in addition to the appropriate requirements specified in IEC 60227-1, which apply to all cables.

The tests for cables specified in the IEC 60227 series are described in IEC 63294.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60227-1:—², *Polyvinyl chloride insulated cables of rated voltages up to and including 450/750 V – Part 1: General requirements*

IEC 60228, *Conductors of insulated cables*

IEC 60332-1-2, *Tests on electric and optical fibre cables under fire conditions – Part 1-2: Test for vertical flame propagation for a single insulated wire or cable – Procedure for 1 kW pre-mixed flame*

IEC 60811-401, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 401: Miscellaneous tests – Thermal ageing methods – Ageing in an air oven*

IEC 60811-405, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 405: Miscellaneous tests – Thermal stability test for PVC insulations and PVC sheaths*

IEC 60811-409, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 409: Miscellaneous tests – Loss of mass test for thermoplastic insulations and sheaths*

IEC 60811-501, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 501: Mechanical tests – Tests for determining the mechanical properties of insulating and sheathing compounds*

IEC 60811-504, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 504: Mechanical tests – Bending tests at low temperature for insulation and sheaths*

² Fourth edition under preparation. Stage at the time of publication IEC FDIS 60227-1:2023.

IEC 60811-505, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 505: Mechanical tests – Elongation at low temperature for insulations and sheaths*

IEC 60811-506, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 506: Mechanical tests – Impact test at low temperature for insulations and sheaths*

IEC 60811-508, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 508: Mechanical tests – Pressure test at high temperature for insulation and sheaths*

IEC 60811-509, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 509: Mechanical tests – Test for resistance of insulations and sheaths to cracking (heat shock test)*

IEC 62440, *Electric cables with a rated voltage not exceeding 450/750 V – Guide to use*

IEC 63294:2021, *Test methods for electric cables with rated voltages up to and including 450/750 V.*