

Edition 1.0 2018-02

# INTERNATIONAL STANDARD

# NORME INTERNATIONALE

Specifications for particular types of winding wires – Part 73: Polyester or polyesterimide overcoated with polyamide-imide enamelled rectangular aluminium wire, class 200

Spécifications pour types particuliers de fils de bobinage – Partie 73: Fil de section rectangulaire émaillé en aluminium revêtu de polyester ou de polyesterimide ainsi que de polyamide-imide, de classe 200

INTERNATIONAL ELECTROTECHNICAL COMMISSION

COMMISSION ELECTROTECHNIQUE INTERNATIONALE

ICS 29.060.10 ISBN 978-2-8322-5416-5

Warning! Make sure that you obtained this publication from an authorized distributor.

Attention! Veuillez vous assurer que vous avez obtenu cette publication via un distributeur agréé.

# CONTENTS

| FOF | REWORD   | 3 |
|-----|--|---|
| INT | RODUCTION  | 5 |
| 1   | Scope  | 6 |
| 2   | Normative references                             | 6 |
| 3   | Terms, definitions, general notes and appearance | 6 |
| 3   | .1 Terms and definitions                         | 6 |
| 3   | .2 General notes                                 | 7 |
|     | 3.2.1 Methods of test                            | 7 |
|     | 3.2.2 Winding wire                               | 7 |
| 3   | .3 Appearance                                    |   |
| 4   | Dimensions                                       |   |
| 5   | Electrical resistance                            |   |
| 6   | Elongation                                       | 7 |
| 7   | Springiness                                      | 7 |
| 8   | Flexibility and adherence                        | 7 |
| 9   | Heat shock                                       | 7 |
| 10  | Cut-through                                      | 7 |
| 11  | Resistance to abrasion                           | 7 |
| 12  | Resistance to solvents                           | 8 |
| 13  | Breakdown voltage                                | 8 |
| 14  | Continuity of insulation                         |   |
| 15  | Temperature index                                | 8 |
| 16  | Resistance to refrigerants                       |   |
| 17  | Solderability                                    |   |
| 18  | Heat or solvent bonding                          |   |
| 19  | Dielectric dissipation factor                    |   |
| 20  | Resistance to transformer oil                    |   |
| 21  | Loss of mass                                     |   |
| 23  | Pin hole test                                    |   |
| 30  | Packaging  |   |
|     | iography   |   |
|     | · - g·p· · j · · · · · · · · · · · · · · · · ·   |   |

### INTERNATIONAL ELECTROTECHNICAL COMMISSION

SPECIFICATIONS FOR PARTICULAR TYPES OF WINDING WIRES –

# Part 73: Polyester or polyesterimide overcoated with polyamide-imide enamelled rectangular aluminium wire, class 200

#### **FOREWORD**

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 60317-73 has been prepared by IEC technical committee 55: Winding wires.

The text of this International Standard is based on the following documents:

| FDIS         | Report on voting |
|--------------|------------------|
| 55/1634/FDIS | 55/1639/RVD      |

Full information on the voting for the approval of this International Standard can be found in the report on voting indicated in the above table.

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts in the IEC 60317 series, published under the general title *Specifications for particular types of winding wires*, can be found on the IEC website.

The numbering of clauses in this standard is not continuous from Clauses 21 through 30 in order to reserve space for possible future wire requirements prior to those for wire packaging.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under "http://webstore.iec.ch" in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

## INTRODUCTION

This part of IEC 60317 forms an element of a series of standards which deals with insulated wires used for windings in electrical equipment. The series has three groups describing:

- 1) Winding wires Test methods (IEC 60851 series);
- 2) Specifications for particular types of winding wires (IEC 60317 series);
- 3) Packaging of winding wires (IEC 60264 series).

# SPECIFICATIONS FOR PARTICULAR TYPES OF WINDING WIRES –

# Part 73: Polyester or polyesterimide overcoated with polyamide-imide enamelled rectangular aluminium wire, class 200

### 1 Scope

This part of IEC 60317 specifies the requirements of enamelled rectangular aluminium winding wire of class 200 with a dual coating. The underlying coating is based on polyester or polyesterimide resin, which can be modified providing it retains the chemical identity of the original resin and meets all specified wire requirements. The superimposed coating is based on polyamide-imide resin.

NOTE A modified resin is a resin that has undergone a chemical change, or contains one or more additives to enhance certain performance or application characteristics.

The range of nominal conductor dimensions covered by this standard is:

width: min. 2,0 mm max. 16,0 mm;
 thickness: min. 0,80 mm max. 5,60 mm.

Wires of grade 1 and grade 2 are included in this specification and apply to the complete range of conductors.

The specified combinations of width and thickness as well as the specified width/thickness ratio are given in IEC 60317-0-9:2015.

#### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60317-0-9:2015, Specifications for particular types of winding wires – Part 0-9: General requirements – Enamelled rectangular aluminium wire

# SOMMAIRE

### COMMISSION ÉLECTROTECHNIQUE INTERNATIONALE

## SPÉCIFICATIONS POUR TYPES PARTICULIERS DE FILS DE BOBINAGE -

# Partie 73: Fil de section rectangulaire émaillé en aluminium revêtu de polyester ou de polyesterimide ainsi que de polyamide-imide, de classe 200

### **AVANT-PROPOS**

- 1) La Commission Electrotechnique Internationale (IEC) est une organisation mondiale de normalisation composée de l'ensemble des comités électrotechniques nationaux (Comités nationaux de l'IEC). L'IEC a pour objet de favoriser la coopération internationale pour toutes les questions de normalisation dans les domaines de l'électricité et de l'électronique. A cet effet, l'IEC entre autres activités publie des Normes internationales, des Spécifications techniques, des Rapports techniques, des Spécifications accessibles au public (PAS) et des Guides (ci-après dénommés "Publication(s) de l'IEC"). Leur élaboration est confiée à des comités d'études, aux travaux desquels tout Comité national intéressé par le sujet traité peut participer. Les organisations internationales, gouvernementales et non gouvernementales, en liaison avec l'IEC, participent également aux travaux. L'IEC collabore étroitement avec l'Organisation Internationale de Normalisation (ISO), selon des conditions fixées par accord entre les deux organisations.
- 2) Les décisions ou accords officiels de l'IEC concernant les questions techniques représentent, dans la mesure du possible, un accord international sur les sujets étudiés, étant donné que les Comités nationaux de l'IEC intéressés sont représentés dans chaque comité d'études.
- 3) Les Publications de l'IEC se présentent sous la forme de recommandations internationales et sont agréées comme telles par les Comités nationaux de l'IEC. Tous les efforts raisonnables sont entrepris afin que l'IEC s'assure de l'exactitude du contenu technique de ses publications; l'IEC ne peut pas être tenue responsable de l'éventuelle mauvaise utilisation ou interprétation qui en est faite par un quelconque utilisateur final.
- 4) Dans le but d'encourager l'uniformité internationale, les Comités nationaux de l'IEC s'engagent, dans toute la mesure possible, à appliquer de façon transparente les Publications de l'IEC dans leurs publications nationales et régionales. Toutes divergences entre toutes Publications de l'IEC et toutes publications nationales ou régionales correspondantes doivent être indiquées en termes clairs dans ces dernières.
- 5) L'IEC elle-même ne fournit aucune attestation de conformité. Des organismes de certification indépendants fournissent des services d'évaluation de conformité et, dans certains secteurs, accèdent aux marques de conformité de l'IEC. L'IEC n'est responsable d'aucun des services effectués par les organismes de certification indépendants.
- 6) Tous les utilisateurs doivent s'assurer qu'ils sont en possession de la dernière édition de cette publication.
- 7) Aucune responsabilité ne doit être imputée à l'IEC, à ses administrateurs, employés, auxiliaires ou mandataires, y compris ses experts particuliers et les membres de ses comités d'études et des Comités nationaux de l'IEC, pour tout préjudice causé en cas de dommages corporels et matériels, ou de tout autre dommage de quelque nature que ce soit, directe ou indirecte, ou pour supporter les coûts (y compris les frais de justice) et les dépenses découlant de la publication ou de l'utilisation de cette Publication de l'IEC ou de toute autre Publication de l'IEC, ou au crédit qui lui est accordé.
- 8) L'attention est attirée sur les références normatives citées dans cette publication. L'utilisation de publications référencées est obligatoire pour une application correcte de la présente publication.
- 9) L'attention est attirée sur le fait que certains des éléments de la présente Publication de l'IEC peuvent faire l'objet de droits de brevet. L'IEC ne saurait être tenue pour responsable de ne pas avoir identifié de tels droits de brevets et de ne pas avoir signalé leur existence.

La Norme internationale IEC 60317-73 a été établie par le comité d'études 55 de l'IEC: Fils de bobinage.

Le texte de cette Norme internationale est issu des documents suivants:

| FDIS         | Rapport de vote |
|--------------|-----------------|
| 55/1634/FDIS | 55/1639/RVD     |

Le rapport de vote indiqué dans le tableau ci-dessus donne toute information sur le vote ayant abouti à l'approbation de cette norme.

Ce document a été rédigé selon les Directives ISO/IEC, Partie 2.

Une liste de toutes les parties de l'IEC 60317, publiées sous le titre général *Spécifications* pour types particuliers de fils de bobinage, peut être consultée sur le site web de l'IEC.

La numérotation des articles de la présente norme n'est pas continue entre les Articles 21 et 30 afin de réserver un espace pour d'éventuelles futures exigences applicables au fil avant celles applicables au conditionnement du fil.

Le comité a décidé que le contenu de ce document ne sera pas modifié avant la date de stabilité indiquée sur le site web de l'IEC sous "http://webstore.iec.ch" dans les données relatives au document recherché. A cette date, le document sera

- · reconduit,
- supprimé,
- remplacé par une édition révisée, ou
- amendé.

## INTRODUCTION

La présente partie de l'IEC 60317 appartient à l'une des séries de normes qui traitent des fils isolés utilisés pour les enroulements des appareils électriques. L'ensemble est composé des trois séries de normes suivantes:

- 1) Fils de bobinage Méthodes d'essai (série IEC 60851);
- 2) Spécifications pour types particuliers de fils de bobinage (série IEC 60317);
- 3) Conditionnement des fils de bobinage (série IEC 60264).

# SPÉCIFICATIONS POUR TYPES PARTICULIERS DE FILS DE BOBINAGE -

# Partie 73: Fil de section rectangulaire émaillé en aluminium revêtu de polyester ou de polyesterimide ainsi que de polyamide-imide, de classe 200

### 1 Domaine d'application

La présente partie de l'IEC 60317 spécifie les exigences relatives aux fils de bobinage de section rectangulaire en aluminium émaillé de classe 200 à double revêtement. La première couche de revêtement est en résine de polyester ou de polyesterimide; elle peut être modifiée à condition de conserver les propriétés chimiques de la résine d'origine et de respecter toutes les exigences spécifiées pour les fils. La deuxième couche de revêtement est en résine de polyamide-imide.

NOTE Une résine modifiée est une résine dont les propriétés chimiques ont été modifiées ou qui contient un ou plusieurs additifs visant à améliorer certaines performances ou caractéristiques d'application.

La plage des dimensions nominales des conducteurs couvertes par la présente norme est:

pour la largeur: min. 2,0 mm max. 16,0 mm;pour l'épaisseur: min. 0,80 mm max. 5,60 mm.

Les fils de grades 1 et 2 sont couverts par la présente spécification et s'appliquent à toute la gamme des conducteurs.

Les combinaisons largeur-épaisseur spécifiées ainsi que le rapport largeur/épaisseur spécifié sont indiqués dans l'IEC 60317-0-9:2015.

### 2 Références normatives

Les documents suivants cités dans le texte constituent, pour tout ou partie de leur contenu, des exigences du présent document. Pour les références datées, seule l'édition citée s'applique. Pour les références non datées, la dernière édition du document de référence s'applique (y compris les éventuels amendements).

IEC 60317-0-9:2015, Spécifications pour types particuliers de fils de bobinage – Partie 0-9: Exigences générales – Fil de section rectangulaire émaillé en aluminium