



IEC/TR 62517

Edition 1.0 2009-04

TECHNICAL REPORT

Magnetizing behaviour of permanent magnets

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

PRICE CODE

R

ICS 29.030

ISBN 2-8318-1037-7

CONTENTS

FOREWORD.....	4
INTRODUCTION.....	6
1 Scope.....	7
2 Effective magnetizing field strength.....	7
3 Initial magnetization state.....	8
4 Magnetizing behaviour of permanent magnets.....	8
4.1 General.....	8
4.2 Nucleation type magnets, sintered Ferrites, RE-Fe-B, SmCo ₅	9
4.2.1 General.....	9
4.2.2 Initial magnetization curve after final heat treatment.....	9
4.2.3 Approach to saturation after final heat treatment.....	9
4.2.4 Coercivity mechanism of nucleation type magnets.....	11
4.2.5 Reversing the magnetization after magnetic saturation.....	12
4.3 Pinning type magnets, Sm ₂ Co ₁₇	13
4.3.1 General.....	13
4.3.2 Initial magnetization curve.....	13
4.3.3 Approach to saturation.....	14
4.3.4 Coercivity mechanism of pinning type magnets.....	15
4.4 Single domain particle magnets.....	16
4.4.1 General.....	16
4.4.2 Single domain particle magnets based on magnetocrystalline anisotropy.....	16
4.4.3 Alnico and CrFeCo magnets.....	16
5 Conclusions.....	17
Bibliography.....	19
Figure 1 – Principal magnetizing behaviour of RE-TM magnets after final heat treatment.....	8
Figure 2 – Magnetizing behaviour of sintered Nd-Dy-Fe-B magnets.....	9
Figure 3 – Magnetizing behaviour of sintered Nd-Dy-Fe-B magnets with various remanence B_r and coercivity H_{cJ} values after final heat treatment.....	11
Figure 4 – Magnetizing behaviour of sintered Nd-Dy-Fe-B magnets with various remanence B_r and coercivity H_{cJ} values after magnetic saturation in the reverse direction.....	12
Figure 5 – Magnetizing behaviour of sintered Sm ₂ Co ₁₇ magnets with a coercivity H_{cJ} of about 800 kA/m.....	13
Figure 6 – Magnetizing behaviour of sintered Sm ₂ Co ₁₇ magnets with a coercivity H_{cJ} of about 2 800 kA/m.....	14
Figure 7 – Magnetizing behaviour of sintered Sm-Co magnets with various remanence B_r and coercivity H_{cJ} values, left: after final heat treatment and right: after magnetic saturation in the reverse direction.....	15
Figure 8 – Magnetization behaviour of bonded anisotropic HDDR RE-Fe-B magnets compared to a sintered anisotropic RE-Fe-B magnet.....	16

Table 1 – The recommended internal magnetizing field strengths, H_{mag} , to achieve complete saturation for modern permanent magnets, starting from the initial state after the final heat treatment 18

INTERNATIONAL ELECTROTECHNICAL COMMISSION

MAGNETIZING BEHAVIOUR OF PERMANENT MAGNETS

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC provides no marking procedure to indicate its approval and cannot be rendered responsible for any equipment declared to be in conformity with an IEC Publication.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

The main task of IEC technical committees is to prepare International Standards. However, a technical committee may propose the publication of a technical report when it has collected data of a different kind from that which is normally published as an International Standard, for example "state of the art".

IEC 62517, which is a technical report, has been prepared by IEC technical committee 68: Magnetic alloys and steels.

The text of this technical report is based on the following documents:

Enquiry draft	Report on voting
68/377/DTR	68/384/RVC

Full information on the voting for the approval of this technical report can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

The committee has decided that the contents of this publication will remain unchanged until the maintenance result date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

A bilingual version of this publication may be issued at a later date.

INTRODUCTION

The full performance of a permanent magnet can only be obtained if it is magnetized properly to saturation. In IEC 60404-5 a definition of the saturation of a permanent magnet is given. Accordingly, a magnet is defined as saturated at a magnetizing field strength H_1 if a 50 % higher field strength leads to an increase of $(BH)_{\max}$ or H_{CB} of less than 1 %. However, such a definition cannot explain the substantial differences in the magnetizing behaviour of modern permanent magnets which is mainly determined by their coercivity mechanisms. Unfortunately the variety of magnetizing behaviours cannot be accommodated by a simple recommendation such as “magnetize with magnetizing field strengths of three to five times the coercivity H_{cJ} ”. In particular for RE permanent magnets with high coercivity H_{cJ} this simplification would lead to unacceptable overestimations of the required magnetizing field strengths.

MAGNETIZING BEHAVIOUR OF PERMANENT MAGNETS

1 Scope

It is within the scope of this technical report to describe the magnetizing behaviour of permanent magnets in detail. Firstly, in Clause 3 the relationship between the applied magnetic field strength and the effectively acting internal field strength is reviewed. In Clause 4 the initial state prior to magnetization is discussed. Then, in the main Clause 5, the magnetizing behaviour of all common types of permanent magnets is outlined. The clause is subdivided according to the dominant coercivity mechanisms, namely the nucleation type for sintered Ferrites, RE-Fe-B and SmCo_5 magnets, the pinning type for carbon steel and $\text{Sm}_2\text{Co}_{17}$ ¹ magnets and the single domain type for nano-crystalline RE-Fe-B, Alnico and Cr-Fe-Co magnets. Finally, the recommended magnetizing field strengths for modern permanent magnets are compiled in a comprehensive table.

¹ The composition $\text{Sm}_2\text{Co}_{17}$ is used as the generic name for a series of binary and multiphase alloys with transition elements such as Fe, Cu and Zr replacing Co, see also IEC 60404-8-1; 2nd edition 2001.