

# TECHNICAL REPORT



---

## Optical fibre cables – Shrinkage effects on cable and cable element end termination – Guidance

INTERNATIONAL  
ELECTROTECHNICAL  
COMMISSION

---

ICS 33.180.10

ISBN 978-2-8322-9434-5

**Warning! Make sure that you obtained this publication from an authorized distributor.**

## CONTENTS

FOREWORD.....	7
INTRODUCTION.....	9
1 Scope.....	10
2 Normative references .....	10
3 Terms and definitions .....	10
4 Abbreviated terms .....	11
5 Characteristics of optical fibre cables .....	11
5.1 General.....	11
5.2 Cable materials.....	11
5.2.1 Plastic materials .....	11
5.2.2 Reversible thermal expansion and contraction .....	11
5.2.3 Irreversible thermal contraction (shrinkage).....	12
5.2.4 Forces between cable elements caused by thermal changes .....	13
5.3 Cable design.....	13
5.4 Basic cable types.....	14
5.5 Cable performance .....	15
5.5.1 General .....	15
5.5.2 Optical performance during temperature changes .....	15
5.5.3 Cable shrinkage characteristic.....	16
5.5.4 Cable shrinkage during connector termination process .....	16
6 Test methods for cable shrinkage .....	17
6.1 General.....	17
6.2 Conditions before shrinkage testing .....	17
6.3 Test method F11.....	17
6.4 Test method F17.....	18
7 Conclusions of the cable shrinkage study .....	19
7.1 General.....	19
7.2 Conclusion for simplex cables.....	19
7.3 Conclusion for loose tube cables .....	20
8 Termination cases of optical fibre cables .....	20
8.1 General.....	20
8.2 Different termination cases .....	20
9 Recommended tests for evaluation of shrinkage effects.....	21
9.1 General.....	21
9.2 Limitation of tests for determination of shrinkage effects .....	22
9.3 Cables terminated with connectors.....	22
9.3.1 Performance indicator tests .....	22
9.3.2 Cable shrinkage.....	22
9.3.3 Cable thermal expansion and contraction .....	22
9.3.4 Cable element forces.....	22
9.4 Cables terminated with hardened connectors .....	22
9.4.1 Performance indicator tests .....	22
9.4.2 Cable shrinkage (fibre protrusion).....	23
9.5 Cables fixed into a module and fibres terminated with connectors.....	23
9.5.1 Performance indicator tests .....	23
9.5.2 Cable shrinkage (fibre protrusion).....	23

9.6	Cables fixed into a divider and fan-out cables terminated with connectors .....	23
9.6.1	Performance indicator tests .....	23
9.6.2	General .....	24
9.6.3	Shrinkage (fibre protrusion) .....	24
9.6.4	Shrinkage of fan-out cable .....	24
9.7	Cables fixed into a protective housing and terminated with splices .....	25
9.7.1	Performance indicator tests .....	25
9.7.2	Cable shrinkage (fibre protrusion) .....	25
9.7.3	Sheath shrinkage .....	25
9.8	Cables fixed into a protective housing and terminated with connectors .....	25
9.8.1	Performance indicator tests .....	25
9.8.2	Cable shrinkage .....	25
10	Recommended test parameters for shrinkage testing and shrinkage grades .....	26
10.1	General .....	26
10.2	Recommended test parameters for shrinkage testing .....	26
10.3	Shrinkage grades for Method F11A .....	27
10.4	Recommended shrinkage limit for Method F11B .....	27
10.5	Fibre protrusion grades for Method F17 .....	27
Annex A (informative)	Test results of the cable shrinkage study .....	29
A.1	General .....	29
A.2	Shrinkage test results of simplex cables .....	29
A.2.1	Simplex cable types for shrinkage tests .....	29
A.2.2	Shrinkage test with different aging methods and duration .....	29
A.2.3	Shrinkage test with various numbers of temperature cycles .....	33
A.2.4	Shrinkage test with different sample lengths .....	34
A.2.5	Shrinkage test versus optical performance of two different simplex cables .....	34
A.2.6	Shrinkage test versus optical performance of different versions of a simplex cable .....	36
A.2.7	Change in length during and after climatic exposure .....	36
A.3	Shrinkage test results for loose tube cables .....	37
A.3.1	Loose tube cable types for shrinkage tests .....	37
A.3.2	Shrinkage test (method F11 modified) of four loose tube cable types .....	37
A.3.3	Shrinkage test (method F17) of four loose tube cable types .....	39
A.3.4	Shrinkage test of nine unitube cable types .....	43
Annex B (informative)	Test method for change in length during climatic exposure .....	45
B.1	General .....	45
B.2	Cable samples .....	45
B.3	Apparatus for determination of the change in length .....	45
B.4	Procedure for determination of the change in length .....	46
B.5	Test results for the change in length .....	46
B.6	Procedure for determination of the change in attenuation .....	47
B.7	Test results for the change in attenuation .....	47
B.8	Comparison of change in length with change in attenuation .....	50
B.9	Conclusion .....	51
Annex C (informative)	Shrinkage testing template .....	52
Annex D (informative)	Recommended tests for performance evaluation of cables to be terminated with connectors .....	53
D.1	General .....	53

D.2	Connector types and design.....	53
D.3	Simplex and duplex cable types .....	55
D.4	Termination of a cable to a connector .....	56
D.5	Overview of recommended cable tests .....	57
D.6	Main performance of a terminated cable .....	57
D.7	Guidance for change of temperature test methods .....	58
Annex E (informative) Recommended tests for performance evaluation of cables to be terminated with hardened connectors.....		59
E.1	General.....	59
E.2	Connector types and design.....	59
E.3	Cable types for hardened connectors .....	59
E.4	Termination of a cable to a hardened connector.....	59
E.5	Overview of recommended cable tests .....	60
E.6	Environmental performance of a terminated cable.....	60
Annex F (informative) Recommended tests for performance evaluation of cables fixed into a module and fibres terminated with connectors .....		61
F.1	General.....	61
F.2	Connector types and design.....	61
F.3	Cable types.....	61
F.4	Termination of a cable to a module .....	61
F.5	Overview of recommended cable tests .....	62
F.6	Main performance of a terminated cable .....	62
Annex G (informative) Recommended tests for performance evaluation of cables fixed into a divider and fan-out cables terminated with connectors.....		63
G.1	General.....	63
G.2	Connector types and design.....	63
G.3	Cable types.....	63
G.3.1	Cables .....	63
G.3.2	Fan-out cables.....	63
G.4	Termination of a cable into a divider and at fan-out cables.....	64
G.5	Overview of recommended cable tests .....	64
G.5.1	Recommended test for cable assembly.....	64
G.5.2	Recommended tests for cables .....	64
G.5.3	Recommended tests for fan-out cables .....	65
Annex H (informative) Recommended tests for performance evaluation of cables fixed into a protective housing and terminated with splices.....		66
H.1	General.....	66
H.2	Types of protective housings.....	66
H.3	Cable types.....	67
H.4	Termination of a cable in a protective housing .....	67
H.5	Overview of recommended cable tests .....	67
H.6	Main performance of a terminated cable .....	68
Annex I (informative) Recommended tests for performance evaluation of cables fixed into a protective housing and terminated with connectors .....		69
I.1	General.....	69
I.2	Types of protective housings.....	69
I.3	Cable types.....	69
I.4	Termination of a cable into a protective housing .....	69
I.5	Overview of recommended cable tests .....	70

I.6	Main performance of a terminated cable .....	70
Annex J (informative)	Recommended test parameters for change of temperature testing .....	71
J.1	Test methods and severities .....	71
J.2	Additional recommendations for the change of temperature test .....	72
Annex K (informative)	Cross-references of cable test methods .....	73
Bibliography	.....	74
Figure 1	– Qualitative example of force during decreasing temperature of two polymer materials.....	13
Figure 2	– Cable sample for shrinkage testing according to Method F11 .....	18
Figure 3	– Cable sample for fibre protrusion testing according to Method F17.....	19
Figure A.1	– Sheath shrinkage in mm of cable type 1 with different temperatures .....	31
Figure A.2	– Sheath shrinkage in mm of cable type 2 with different temperatures .....	32
Figure A.3	– Sheath shrinkage in mm of cable type 3 with different temperatures .....	33
Figure A.4	– Sheath shrinkage at different number of cycles .....	34
Figure A.5	– Change in attenuation during temperature cycling.....	35
Figure A.6	– Change in attenuation versus sheath shrinkage .....	36
Figure A.7	– Preparation of sample and measured lengths .....	38
Figure A.8	– Shrinkage of sheath and loose tube after different number of cycles .....	39
Figure A.9	– Preparation of sample and measured or calculated protrusion lengths .....	40
Figure A.10	– Protrusion length of cable type 1.....	41
Figure A.11	– Protrusion length of cable type 2.....	41
Figure A.12	– Protrusion length of cable type 3.....	42
Figure A.13	– Protrusion length of cable type 4.....	42
Figure A.14	– Change of fibre protrusion.....	44
Figure B.1	– Apparatus for holding cable samples .....	45
Figure B.2	– Temperature cycle with measurement points .....	46
Figure B.3	– Cable sheath length measurement results .....	47
Figure B.4	– Change in attenuation of orange cable samples at 1 310 nm .....	48
Figure B.5	– Change in attenuation of orange cable samples at 1 550 nm .....	48
Figure B.6	– Change in attenuation of orange cable samples at 1 625 nm .....	49
Figure B.7	– Change in attenuation of yellow cable samples at 1 310 nm.....	49
Figure B.8	– Change in attenuation of yellow cable samples at 1 550 nm.....	50
Figure B.9	– Change in attenuation of yellow cable samples at 1 625 nm.....	50
Figure D.1	– Cable terminated with connector plug .....	53
Figure D.2	– LC connector variants.....	53
Figure D.3	– Simplex cable terminated at LC simplex connector .....	54
Figure D.4	– Fibre movement in spring-loaded connectors.....	55
Figure D.5	– Simplex cable type .....	55
Figure D.6	– Duplex cable types .....	56
Figure D.7	– Test arrangement for method F12.....	58
Figure E.1	– Cable terminated with hardened connector .....	59
Figure F.1	– Cable fixed into a module and terminated with connectors .....	61

Figure G.1 – Cable fixed into a divider and fan-out cables terminated with connectors.....	63
Figure H.1 – Cable fixed into a protective housing and terminated with splices .....	66
Figure I.1 – Cable fixed into a protective housing and terminated with connectors .....	69
Figure J.1 – Change of temperature test configuration .....	72
Table 1 – Linear coefficients of thermal expansion of materials (informative) .....	12
Table 2 – Typical characteristics of indoor and outdoor cables.....	15
Table 3 – Overview of different termination cases .....	21
Table 4 – Temperature cycling severities for shrinkage testing for Methods F11A and F17 .....	27
Table 5 – Recommended sheath shrinkage grades .....	27
Table 6 – Recommended change of fibre protrusion $\Delta L_1$ grades .....	28
Table 7 – Recommended change of fibre protrusion $\Delta L_2$ grades .....	28
Table A.1 – Overview of shrinkage results .....	34
Table A.2 – Overview of simplex results.....	35
Table A.3 – Details of loose tube cable types.....	37
Table A.4 – Details of unitube cable types .....	43
Table B.1 – Comparison of change in length with change in attenuation .....	51
Table C.1 – Shrinkage testing template.....	52
Table D.1 – Recommended tests for cables to be terminated with connectors.....	57
Table E.1 – Recommended tests for cables to be terminated with hardened connectors.....	60
Table F.1 – Recommended tests for cables fixed into module and terminated with connectors.....	62
Table G.1 – Recommended tests for cable assembly .....	64
Table G.2 – Recommended tests for cables fixed into dividers.....	64
Table G.3 – Recommended tests for fan-out cables .....	65
Table H.1 – Recommended tests for cables fixed at protective housing and terminated with splices .....	67
Table I.1 – Recommended tests for cables fixed into a protective housing and terminated with connectors .....	70
Table J.1 – Severities for change of temperature testing.....	71
Table K.1 – Cross reference table of mechanical test methods .....	73
Table K.2 – Cross reference table of environmental test methods .....	73

## INTERNATIONAL ELECTROTECHNICAL COMMISSION

**OPTICAL FIBRE CABLES –  
SHRINKAGE EFFECTS ON CABLE AND CABLE  
ELEMENT END TERMINATION – GUIDANCE**

## FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

The main task of IEC technical committees is to prepare International Standards. However, a technical committee may propose the publication of a Technical Report when it has collected data of a different kind from that which is normally published as an International Standard, for example "state of the art".

IEC TR 62959, which is a Technical Report, has been prepared by subcommittee 86A: Fibres and cables, of IEC technical committee 86: Fibre optics.

The text of this technical report is based on the following documents:

Enquiry draft	Report on voting
86A/2032/DTR	86A/2058/RVDTR

Full information on the voting for the approval of this technical report can be found in the report on voting indicated in the above table.

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under "<http://webstore.iec.ch>" in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

**IMPORTANT – The "colour inside" logo on the cover page of this document indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.**



## INTRODUCTION

Cable shrinkage is sometimes used as a part of the performance criteria for optical fibre cables, including standard glass optical fibres for telecommunication application. However, there is only a partial correlation between shrinkage and other important cable parameters such as temperature performance and optical transmission characteristics, particularly during mechanical and environmental stress, since shrinkage strongly depends on the cable materials, the cable construction and the manufacturing processes.

The environmental performance of optical fibre cables is mainly determined using a suitable temperature cycling test while continuously measuring the change in attenuation during and after the test. Low shrinkage performance is not guaranteed by such a test method, so any cable shrinkage observed during and/or after the temperature cycle test can be used as an additional indicator for the characterisation of cables.

Cable shrinkage should be understood to include shrinkage of the entire cable, shrinkage of cable sub-assemblies such as units, and shrinkage of cable elements. It should also be understood that shrinkage of portions of the cable might be expressed as "growth" of other elements, such as fibres, strength members. Specific issues of cable shrinkage – buffer shrinkage, strength member growth, sheath shrinkage, etc. – should be carefully addressed when applying the principles of this document.

A combination of the passive component design (connectors, passive components, protective housings or cable management components) and cable shrinkage influences the cable/component performance. Excessive shrinkage at the cable/device interface can cause extra process steps and/or extra precautions to be taken at the interface and can cause degradation of the interface in service, for example the failure of strain relief effectiveness at a connector as the sheath shrinks back in use compromising the continuously optimal optical transmission parameters. Component manufacturers use a number of compensations for cable shrinkage in the design or assembly process of their components and will often select cables used in finished components for their low shrinkage performance. On the other hand, shrinkage can be compensated by installation technique.

To cover all relevant aspects of cables to be terminated, the recommended tests for performance evaluation of cables for different termination cases in addition to the optional tests for evaluation of shrinkage effects are included in this document.

This study into cable shrinkage was triggered by a CENELEC/TC86 BXA liaison letter sent to IEC/SC 86A in April 2016. The letter pointed out observed inconsistencies in indoor cable standards from a user point of view and asked for their concerns and recommendations to be addressed. The main subject was that jacket shrinkage should be a specified parameter for all indoor cables that are normally terminated by connectors, passive components or closures/enclosures.

A correspondence group in IEC/SC 86A/WG 3 was formed in 2016 to address issues about cable shrinkage. After discussion about relevant issues, cable shrinkage tests were performed, and the test results were collected and recorded. Annex A shows these test results and Clause 7 gives the conclusions of the cable shrinkage study. Generally, optical fibre cable types with a small outer diameter were involved in shrinkage testing. The results of different cable types from only a few cable manufactures were included, hence the number of cable types was limited and does not represent all cable types in the worldwide market. Subsequent work was done on recommendations for performance evaluation of cables to be terminated with connectors.

## **OPTICAL FIBRE CABLES – SHRINKAGE EFFECTS ON CABLE AND CABLE ELEMENT END TERMINATION – GUIDANCE**

### **1 Scope**

This document, which is a Technical Report, provides information on cable shrinkage characterisation of optical fibre cables that consist of standard glass optical fibres for telecommunication application. The characterisation is directed to the effects of cable shrinkage or cable element shrinkage on the termination of cables. Shrinkage can or cannot be a concern depending on the method of termination. Examples of different cable termination cases are included and described. Tests for the evaluation of cable shrinkage are recommended that can be used as indicators, and shrinkage classification by several grades are given.

### **2 Normative references**

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60794-1-1, *Optical fibre cables – Part 1-1: Generic specification – General*