

TECHNICAL REPORT

Electrical steel – Reverse bend test method for electrical steel strip and sheet

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

ICS 29.030

ISBN 978-2-8322-5616-9

Warning! Make sure that you obtained this publication from an authorized distributor.

CONTENTS

FOREWORD.....	3
INTRODUCTION.....	5
1 Scope.....	6
2 Normative references	6
3 Terms and definitions	6
4 Symbols and designations	7
5 Principles	7
6 Apparatus.....	7
7 Test specimen	8
8 Procedure.....	8
9 Expression of results	10
Annex A (informative) An example of the apparatus used for the reverse bend test	11
Annex B (informative) Dependence of the number of bends on tensile force applied to the test specimen.....	13
B.1 General.....	13
B.2 Test results.....	13
B.3 Deformation situation of the specimen after failure.....	14
B.4 Conclusions	15
Bibliography.....	16
Figure 1 – Apparatus for the reverse bend test of Mode A and Mode B	7
Figure 2 – Schematic view of the mandrels for Mode A and Mode B	8
Figure 3 – Method of counting reverse bends.....	9
Figure A.1 – Schematic view of a specially designed apparatus for the reverse bend test	11
Figure B.1 – Number of bends for different tensile forces with Mode A.....	13
Figure B.2 – Number of bends for different tensile forces with Mode B.....	14
Figure B.3 – Side views of the specimens after failure with Mode A and Mode B for different tensile forces	14

INTERNATIONAL ELECTROTECHNICAL COMMISSION

**ELECTRICAL STEEL –
REVERSE BEND TEST METHOD FOR
ELECTRICAL STEEL STRIP AND SHEET****FOREWORD**

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

The main task of IEC technical committees is to prepare International Standards. However, a technical committee may propose the publication of a technical report when it has collected data of a different kind from that which is normally published as an International Standard, for example "state of the art".

IEC TR 63114, which is a technical report, has been prepared by IEC Technical Committee 68: Magnetic alloys and steels.

The text of this technical report is based on the following documents:

Enquiry draft	Report on voting
68/565/DTR	68/579A/RVDTR

Full information on the voting for the approval of this technical report can be found in the report on voting indicated in the above table.

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under "<http://webstore.iec.ch>" in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

A bilingual version of this publication may be issued at a later date.

INTRODUCTION

Before the preparation of this document, the working group discussed the actual situation of industry concerning the application of reverse bend tests for the evaluation of the ductility of electrical steel strip and sheet, including non-oriented and grain-oriented materials. The following points were noted:

- The reverse bend test is widely used in industry for the evaluation of ductility of electrical steel, and is referenced by the products standards;
- In actual industry practice, the reverse bend test mainly uses as test specimens Epstein strips of 30 mm in width;
- The product standards of IEC 60404-8-4 [1]¹, IEC 60404-8-7 [2] and IEC 60404-8-8 [3] refer to ISO 7799 for the reverse bend test. However, ISO 7799 specified the width of test specimen to be less than the width of the Epstein strip (30 mm). Therefore, the Epstein strip does not meet with the requirement of ISO 7799;
- There are two modes for the reverse bend test, Europe generally adopts the method of reverse bend test according to ISO 7799 (defined as Mode A), alternatively America and Asia generally adopt that according to ASTM A720 [4] (for non-oriented materials) and JIS C2550 [5] (defined as Mode B), see also the references [6-7];

NOTE ASTM A721 [8] defined a bend method, which is different from the reverse bend test, to determine the ductility of grain-oriented materials.

- The apparatus and the requirements for the reverse bend test are slightly different between Mode A and Mode B, especially on the gap between the specimen and the round edges of the clamp and the requirement that a tensile force is applied to the test specimen; This may cause different deformation mechanisms during bending;
- A comparison test between the two modes has been carried out. It was revealed that number of bends obtained with Mode A and Mode B are different.

The above points indicate the need for a standardization of the reverse bend test method particular to electrical steel to explain how to use the two modes in industry.

This document describes the general principle and technical details of the reverse bend test especially for the evaluation of the ductility of electrical steel with respect to the two modes, Mode A according to ISO 7799 and Mode B according to ASTM A720 and JIS C2550.

Annex A provides information on a specially designed apparatus for the reverse bend test, which can be used for both modes.

Annex B gives test results on the dependence of the number of bends on the tensile force applied to the specimen. The results were obtained using the apparatus described in Annex A in different conditions for Mode A and for Mode B.

¹ Numbers in square brackets refer to the Bibliography.

ELECTRICAL STEEL – REVERSE BEND TEST METHOD FOR ELECTRICAL STEEL STRIP AND SHEET

1 Scope

This Technical Report describes the general principle and technical details of the reverse bend test method used for evaluating the ductility of electrical steel strip and sheet.

This test method is applicable to Epstein test strip specimens obtained from non-oriented and grain-oriented electrical steel of any grade. The test specimens shall not be annealed.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60404-2, *Magnetic materials – Part 2: Methods of measurement of the magnetic properties of electrical steel strip and sheet by means of an Epstein frame*

ISO 7799, *Metallic materials – Sheet and strip 3 mm thick or less – Reverse bend test*