



Edition 1.0 2018-08

TECHNICAL SPECIFICATION



Nanomanufacturing – Key control characteristics – Part 4-7: Nano-enabled electrical energy storage – Determination of magnetic impurities in anode nanomaterials, ICP-OES method

INTERNATIONAL ELECTROTECHNICAL COMMISSION

ICS 07.120; 07.030

ISBN 978-2-8322-5971-9

Warning! Make sure that you obtained this publication from an authorized distributor.

CONTENTS

FOREWO)RD	4
INTRODU	JCTION	6
1 Scop	De	7
2 Norn	native references	7
3 Term	ns and definitions	7
	view of the measurement	
	gents	
	-	
5.1	Nitric acid Hydrochloric acid	
5.2	•	
5.3 5.4	Nitrohydrochloric acid Ethanol	
5.4 5.5	Argon gas	
5.6	Standard solutions	
5.6.1		
5.6.2		-
5.6.3		
5.6.4		
	aratus	
6.1 6.2		
6.2	Conical flask	
6.3 6.4	Sample tank	
0.4 6.5	Electronic balance	
0.5 6.6	Scroll equipment	
6.7	Ultrasonic cleaning equipment	
6.8	Heating device	
	paration of series of standard solutions	
•	procedure	
8.1	Cleaning the magnet	
8.2	Test sample	
8.3	Attraction of magnetic impurities	
8.4	Remove nonmagnetic impurities	
8.5	Extraction of magnetic impurities	
8.6	Preparation of blank sample	
8.7	Test	
	analysis and calculation of results	
	report	
	(informative) Diagram of the scroll device	
Annex B	(informative) Magnet removal method	14
Annex C	(informative) Case study	15
C.1	Preparation of series of standard solutions	15
C.2	Cleaning the magnet	15
C.3	Weighing sample	15
C.4	Attraction of magnetic impurities	16
C.5	Remove nonmagnetic impurities	16

C.6	Extraction of magnetic impurities	17
C.7	Test	
C.8	Identify the uncertainty sources	
Annex D	(informative) Validation of the attraction procedure	
D.1	Experimental samples	
D.2	Experimental procedure	
D.3	Experimental results and conclusion	
Bibliogra	ɔhy	20

Figure A.1 – Diagram of sample tank on the rolling device	13
Figure B.1 – Diagram of magnet removal	14
Figure C.1 – Procedure for cleaning the magnet	15
Figure C.2 – Procedure for weighing sample	16
Figure C.3 – Procedure for attraction of magnetic impurities	16
Figure C.4 – Procedure for removing nonmagnetic impurities	17
Figure C.5 – Procedure for extraction of magnetic impurities	17

Table 1 – Recommended test wavelengths for the determination of magnetic impurities	9
Table 2 – Correspondence of the measured mass to the untapped bulk density of the sample	10
Table 3 – Instrument operating parameters	11
Table C.1 – Test results of magnetic impurities	18
Table D.1 – Test results of magnetic impurities	19

INTERNATIONAL ELECTROTECHNICAL COMMISSION

NANOMANUFACTURING – KEY CONTROL CHARACTERISTICS –

Part 4-7: Nano-enabled electrical energy storage – Determination of magnetic impurities in anode nanomaterials, ICP-OES method

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

The main task of IEC technical committees is to prepare International Standards. In exceptional circumstances, a technical committee may propose the publication of a Technical Specification when

- the required support cannot be obtained for the publication of an International Standard, despite repeated efforts, or
- the subject is still under technical development or where, for any other reason, there is the future but no immediate possibility of an agreement on an International Standard.

Technical Specifications are subject to review within three years of publication to decide whether they can be transformed into International Standards.

IEC TS 62607-4-7, which is a Technical Specification, has been prepared by IEC technical committee 113: Nanotechnology for electrotechnical products and systems.

The text of this Technical Specification is based on the following documents:

Enquiry draft	Report on voting
113/405/DTS	113/430/RVDTS

Full information on the voting for the approval of this Technical Specification can be found in the report on voting indicated in the above table.

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts in the IEC TS 62607 series, published under the general title *Nanonmanufacturing – Key control characteristics*, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under "http://webstore.iec.ch" in the data related to the specific document. At this date, the document will be

- transformed into an International Standard,
- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

A bilingual version of this publication may be issued at a later date.

IMPORTANT – The 'colour inside' logo on the cover page of this publication indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.

INTRODUCTION

Magnetic impurities often have significant influence on the performance of anode nanomaterials for nano-enabled electrical energy storage. If anode nanomaterials have high magnetic impurity content, it may lead to serious self-discharge and degrade the performance and cycle life. The magnetic impurities are also easy to aggregate, which can cause safety issues such as internal short-circuit fire, or even explosion. Therefore, accurate evaluation of magnetic impurity content is important for the safety and performance of energy storage devices. [1,2,3]¹

Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES) method is a mature and precise method to measure the concentration of metal elements in the tested materials, but the method to gather the magnetic substance has not been standardized. This document introduces a reliable method for gathering and determining the magnetic impurity content in the anode nanomaterials of an energy storage device. It will help to better control the quality of electrode nanomaterials.

This document introduces a determination of magnetic impurities using ICP-OES method for the electrochemical characterization of nano-enabled anode materials for electrical energy storage devices.

This standardized method is intended for use in comparing the characteristics of anode nanomaterials in the study stage, not for evaluating the electrode in end products.

The method is applicable to materials exhibiting function or performance only possible with nanotechnology, intentionally added to the active materials to measurably and significantly change the reliability or one or more physical properties of electrical energy storage devices.

In this context it is important to note that the percentage content of nanomaterials of the device in question has no direct relation to the applicability of this document, because minute quantities of nanomaterials are frequently sufficient to improve the performance significantly.

The fraction of nanomaterials in electrodes or electrode coatings is not of relevance for using this method.

¹ Numbers in square brackets refer to the Bibliography.

NANOMANUFACTURING – KEY CONTROL CHARACTERISTICS –

Part 4-7: Nano-enabled electrical energy storage – Determination of magnetic impurities in anode nanomaterials, ICP-OES method

WARNING – Persons using this method should be familiar with normal laboratory practice. This document does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to ensure compliance with any national regulatory conditions.

IMPORTANT – It is absolutely essential that tests conducted according to this document be carried out by suitably trained staff.

1 Scope

This part of IEC TS 62607 provides a method for the determination of magnetic impurities in anode nanomaterials for energy storage devices using an Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES), including test overview, reagents, apparatus, test procedures, test results and test report.

This document applies to the determination of the total content of magnetic impurities (iron, cobalt, chromium, and nickel) ≥ 0.02 mg/kg which can be attracted by magnet.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3696:1987, Water for analytical laboratory use – Specification and test methods

ISO 6353-1:1982, Reagents for chemical analysis – Part 1: General test methods

ISO 18842:2015, Aluminium oxide primarily used for the production of aluminium – Method for the determination of tapped and untapped density