

TECHNICAL SPECIFICATION



**Measurement procedures for materials used in photovoltaic modules –
Part 6-3: Adhesion testing for PV module laminates using the single
cantilevered beam (SCB) method**

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

ICS 27.160

ISBN 978-2-8322-5561-2

Warning! Make sure that you obtained this publication from an authorized distributor.

CONTENTS

FOREWORD.....	4
INTRODUCTION.....	6
1 Scope.....	7
2 Normative references	7
3 Terms and definitions	7
4 Apparatus.....	9
4.1 Load frame	9
4.2 Loading tab.....	10
5 Width-tapered cantilever beam	10
5.1 General.....	10
5.2 Beam design.....	11
5.3 Beam selection	11
6 Test method	12
6.1 Specimen preparation	12
6.2 Measurement procedure	12
6.3 Analysis.....	14
6.3.1 Critical adhesion energy, G_C	14
7 Report	15
Annex A (informative) Summary of background theory, and how this method can be generalized.....	16
A.1 Background theory.....	16
A.2 Beam materials.....	17
Annex B (informative) Guidance for specific use cases	18
B.1 General.....	18
B.2 Adhesion test coupons.....	18
B.2.1 Backsheet / encapsulant adhesion.....	18
B.2.2 Backsheet interlayer adhesion	18
B.2.3 Glass/encapsulant adhesion	19
B.2.4 Adhesion between different encapsulants	19
B.2.5 Cell/encapsulant (coupons)	20
B.3 Modules	20
B.3.1 General	20
B.3.2 Targeting a specific interface in a module.....	20
Annex C (informative) Reference engineering diagrams for loading tab and beam	23
Annex D (normative) Using a reference compliance curve to calculate G_C	26
D.1 General.....	26
D.2 Procedure	26
D.2.1 Beam compliance measurement	26
D.2.2 Definition of empirical parameters.....	27
D.2.3 Validation of reference parameters	27
D.2.4 Generating a custom set of α , β and γ parameters.....	28
D.2.5 Calculation of crack length a_i for adhesion specimens	29
Annex E (informative) Methods for measurement of final debond length a_f	30
E.1 General.....	30
E.2 Aluminum foil method.....	30

E.3 Light method 30

E.4 Pull-apart method 30

Bibliography 32

Figure 1 – Diagram of the loading connection using a clevis grip9

Figure 2 – Schematic of load frame with a) a platen for securing test coupon, and b) modified to sit on top of a PV module 10

Figure 3 – Photos of the loading tab alone, and attached to the beam 10

Figure 4 – Width-tapered beam 11

Figure 5 – Typical width-tapered cantilever beam load/displacement curve 13

Figure 6 – Example of an a_f measurement on glass/encapsulant/cell specimens 14

Figure B.1 – Top view of backsheet and encapsulant beam coupons 21

Figure B.2 – Cross-sectional view of backsheet and encapsulant beam coupons 22

Figure C.1 – Schematics of loading tab 24

Figure C.2 – Schematics of beam 25

Figure D.1 – Photo of a beam prior to start of the calibration measurement 26

Figure D.2 – Photo of a beam at the end of the calibration measurement 27

Figure D.3 – Plot used for generating beam calibration curves with the empirical fits according to Formula (D.2) using values from Table D.1 29

Figure E.1 – Illustration of debond length measurement with a cohesive zone 31

Table 1 – Typical adhesion strengths 12

Table D.1 – Reference empirical fit parameters 27

Table D.2 – Example read points for fit evaluation 28

INTERNATIONAL ELECTROTECHNICAL COMMISSION

**MEASUREMENT PROCEDURES FOR MATERIALS
USED IN PHOTOVOLTAIC MODULES –**
**Part 6-3: Adhesion testing for PV module laminates
using the single cantilevered beam (SCB) method**
FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as “IEC Publication(s)”). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

IEC TS 62788-6-3 has been prepared by IEC technical committee 82: Solar photovoltaic energy systems. It is a Technical Specification.

The text of this Technical Specification is based on the following documents:

Draft	Report on voting
82/2012/DTS	82/2057A/RVDTS

Full information on the voting for its approval can be found in the report on voting indicated in the above table.

The language used for the development of this Technical Specification is English.

This document was drafted in accordance with ISO/IEC Directives, Part 2, and developed in accordance with ISO/IEC Directives, Part 1 and ISO/IEC Directives, IEC Supplement, available at www.iec.ch/members_experts/refdocs. The main document types developed by IEC are described in greater detail at <http://www.iec.ch/standardsdev/publications>.

A list of all parts in the IEC 62788 series, published under the general title *Measurement procedures for materials used in photovoltaic modules*, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under webstore.iec.ch in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

IMPORTANT – The "colour inside" logo on the cover page of this document indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.

INTRODUCTION

This document describes the single cantilevered beam (SCB) test, useful for characterizing adhesion in photovoltaic (PV) modules. This method is grounded in fundamental concepts of beam and fracture mechanics [1]¹, [4], and allows for a quantitative measurement of adhesion strength. A method for calculating the debond length, a_f , has been developed as an option to physical measurement.

PV modules are multi-layer structures that depend on adequate adhesion between each layer to ensure their reliable operation. Adhesion testing is described in current IEC PV standards for module safety qualification (IEC 61730-2) and component characterization (IEC 62788 series). The most commonly used tests are peel tests at either 180° for components (IEC TS 62788-2 test and IEC 62788-1-1), or at 90° for modules (IEC 61730-2 MST 35).

Peel tests are in practice simple to carry out, and provide a peel strength value, different from adhesion strength. Viscoelastic properties of the polymeric material and the mechanics of the pull tab have a strong influence on the result, making these tests of limited value in comparing either different materials, or the same material after stress exposures.

In the SCB method, an elastic width-tapered cantilever beam is adhered to the sample. When the beam is loaded at its apex, delamination will initiate at the weakest interface and advance upon continued loading. This measurement allows for calculation of the critical value of the energy release rate, G_c , which is the adhesion property for a given material interface. The value defined by this method is less dependent of the viscoelastic properties of the polymeric material, and so more useful for measuring differences or changes in adhesive strength.

The SCB method can be conducted at either the coupon or module level. Because it does not require using the backsheet as a pull tab, it is more likely to be able to test the adhesion of a thin outer layer of the backsheet. These considerations give this test method good flexibility to use in applications related to PV modules. Examples for several specific use cases are provided.

This document offers a generalized method for performing the test, with the expectation that best practices for utilizing this test method will be developed for specific applications.

Examples of this method being employed to quantify and define the threshold values of encapsulant and backsheet adhesion for PV module reliability may be found in the literature [1] through [5].

¹ Numbers in square brackets refer to the Bibliography.

MEASUREMENT PROCEDURES FOR MATERIALS USED IN PHOTOVOLTAIC MODULES –

Part 6-3: Adhesion testing for PV module laminates using the single cantilevered beam (SCB) method

1 Scope

This part of IEC TS 62788 provides a method for measuring the adhesion energy of most interfaces within the photovoltaic (PV) module laminate.

In contrast to other adhesion tests in general use, this method provides a measure of adhesive energy, via the critical energy release rate, and so is more useful for comparing adhesion of different specimen types; e.g. different materials, module or coupon samples, or materials before and after stress exposure.

This is a “weakest link” test, meaning that the weakest interface is the one most likely to fail in a given test. Adhesion of a specific layer may be difficult to intentionally measure if there is a weaker interface in the system.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC TS 61836, *Solar photovoltaic energy systems – Terms, definitions and symbols*

ISO 7500-1, *Metallic materials – Calibration and verification of static uniaxial testing machines – Part 1: Tension/compression testing machines – Calibration and verification of the force-measuring system*